



City Research Online

## City, University of London Institutional Repository

---

**Citation:** Nasir Bashir, M., Saad, H. M., Rizwan, M., Bingöl, S., Channa, I. A., Gul, M., Haseeb, A. S. M. A. & Naher, S. (2022). Effect of cobalt nanoparticles on mechanical properties of Sn–58Bi solder joint. *Journal of Materials Science: Materials in Electronics*, 33(28), pp. 22573-22579. doi: 10.1007/s10854-022-09035-6

This is the accepted version of the paper.

This version of the publication may differ from the final published version.

---

**Permanent repository link:** <https://openaccess.city.ac.uk/id/eprint/31388/>

**Link to published version:** <https://doi.org/10.1007/s10854-022-09035-6>

**Copyright:** City Research Online aims to make research outputs of City, University of London available to a wider audience. Copyright and Moral Rights remain with the author(s) and/or copyright holders. URLs from City Research Online may be freely distributed and linked to.

**Reuse:** Copies of full items can be used for personal research or study, educational, or not-for-profit purposes without prior permission or charge. Provided that the authors, title and full bibliographic details are credited, a hyperlink and/or URL is given for the original metadata page and the content is not changed in any way.

---

City Research Online:

<http://openaccess.city.ac.uk/>

[publications@city.ac.uk](mailto:publications@city.ac.uk)

---

# Effect of Cobalt Nanoparticles on Mechanical Properties of Sn-58Bi Solder Joint

M. Nasir Bashir<sup>1</sup>, Hafiz Muhammad Saad<sup>2</sup>, Muhammad Rizwan<sup>3</sup>, Sedat Bingöl<sup>4</sup>, Iftikhar Ahmed Channa<sup>5</sup>, Mustabshirha Gul<sup>6</sup>, A.S.M.A. Haseeb\*<sup>7</sup>, Sumsun Naher\*<sup>8</sup>.

1,2. National University of Sciences and Technology, Islamabad, Pakistan

3,5. Department of Metallurgical Engineering NEDUET, Pakistan

4. Department of Mechanical Engineering, Dicle University, Diyarbakir, Turkey

6. Mechanical Engineering department, Faculty of Engineering and Technology, Bahauddin Zakariya University, Multan, Pakistan

7. Department of Mechanical Engineering, University of Malaya, Kuala Lumpur, 50603, Malaysia

8. Department of Mechanical Engineering and Aeronautics, City, University of London, London, United Kingdom

Email of Corresponding Author: haseeb@um.edu.my  
sumsun.naher.1@city.ac.uk

## Abstract

Brittle phases are responsible for crack formation and propagation in tin-bismuth (Sn-58Bi) solder material. The purpose of this work is to investigate the effects of various cobalt (Co) nanoparticle (NP) concentrations on the tensile properties of the Sn-58Bi solder matrix. Different aging times were studied to find out the effect of Co NP on ultimate tensile strength. Tin-Bismuth solder joints of different Co NP concentrations of 0%, 0.5%, 1% and 2% were prepared. The reflow process was done at 180°C for 1 minute. Scanning Electron Microscopy and Energy Dispersive X-ray spectroscopy were used to analyze the solder joints. The tensile test was carried out for the Sn-58Bi and Sn-58Bi-xCo ( $x = 0.5, 1$  and  $2$ ) solder joints. The tensile test was run before and after aging time. The tensile results reveal that the addition of Co NP increased the tensile strength significantly at different concentrations of Co NP. The

Tensile test revealed that ductility was improved as the temperature was increased. As the aging time increased, the ultimate tensile strength of all samples decreased.

**Keywords:** Tensile Test, Ultimate Tensile Strength, Strain Rate, Ductility.

## **INTRODUCTION**

In microelectronic packaging, solders not only provide electronic connections but also ensure mechanical properties, which is crucial for the operation of electronic devices. However, with the trend toward functional and miniaturized devices, solder joint reliability is becoming more and more concerned [1]. Despite this, high circuit density device chips produced a considerable amount of Joule heat due to their increasing functionality. For bonding, we need solder materials with a lower melting point [2]. Lead-based solders are the best option since they possess a lower melting point [3]. The lead-based solder materials used earlier were highly toxic, so it was found in the 1970s that lead-free materials be used instead of Pb-based solders [4, 5].

Recent research had found several Pb-free solder materials instead of Pb-based solders, and most of them are tin-based alloys [6]. One suggested solder material is a tin-bismuth (Sn-Bi) alloy that has eutectic or near eutectic composition [7]. Sn-Bi solder alloy was considered in place of Sn-Pb alloy because it has the same mechanical properties at a lower temperature and has a melting point that is lower than Sn-Pb solder alloy. It helps reduce thermal damage to the chips during the reflow process [8, 9]. Chips can generate heat during the use of the electronic device, which can damage the solder joints. In solder, atoms diffuse faster as the homologous temperature increases, causing their mechanical properties to decline. As the mechanical properties decrease, deformation issues can arise in a solder joint [10, 11].

Researchers have investigated several techniques for improving the mechanical properties of the Sn-Bi solder matrix, including adding alloying elements [12], adding microparticles [13],

adding nanoparticles (NP) [14-20] and adding carbon nanotubes [21]. A number of elements have been added to the Sn-Bi, including Y [22], Ce [23] and Ti [24]. Researchers used Sn-Bi solder matrix with Ag [25], Au [26], and Zn [27] to improve mechanical properties. Ni was also added to the Sn-Bi solder matrix by some researchers [28-30], and they found significant improvements in the mechanical properties of the solder joints. Less attention has been given to the effects of adding cobalt (Co) into Sn-Bi. Co, being one of the possible candidates, could enhance the mechanical properties of the Sn-Bi solder matrix [31]. Previous studies investigated the effect of cobalt on SAC305 solder joint and observed that cobalt improved the microstructural and mechanical properties of the solder joint [32]. To understand the effects of mechanical properties on the Sn-58Bi-Co system, tensile stress, tensile strain, maximum tensile strength, and elongation following Co addition to the system are required. It is necessary to comprehend the effect of Co NP on microstructural and mechanical properties of the Sn-Bi solder joint. As no research has been done on Co NP added to Sn-Bi alloy solders, this study investigated the tensile properties of Sn-58Bi solder alloys with different amounts of Co NP.

The objective of this work is to investigate how Co NP addition affects the tensile properties of the Sn-58Bi solder joint. Changes in microstructure were observed after reflow. Tensile tests were conducted after reflow to study how Co NP affects the Sn-58Bi solder joint. Different aging times were studied to find out the effect of Co NP on ultimate tensile strength.

## **METHODOLOGY**

Solder paste and copper bar preparation are the first steps in the process. One end of the copper bar was cleaned and polished to remove the oxide layer. After grounding, the copper bar was cleaned with distilled water and 20% sulphuric acid ( $H_2SO_4$ ) to remove any oxide and stain. Tensile samples with different percentages of Co NP of size 28 nm addition into Sn-58Bi solder paste were prepared. Around 1 mm thickness between the two copper bars was created to allow

the solder paste to insert into the space created. Solder paste with different Co NP was added between the two copper bars as shown in Figure 1 (a). The aluminum plates were used to fix the position of the copper bars in Fig 1 (b). The plate was then put into the reflow oven at 180°C for 1 minute to undergo a reflow process. The variation of temperature was kept at  $\pm 5^\circ\text{C}$ . After the reflow process, the excess solder on the surface was removed manually to prevent the excess solder affect the tensile test result. Figure 1 (c) shows the tensile samples of Sn-58Bi. A tensile test was performed by using the universal tensile machine (UTM). A Strain rate of  $6.96 \times 10^{-4} \text{ s}^{-1}$  was applied to pull the samples. After the samples fractured, the results were collected and analyzed. Different aging times were used to determine the impact of Co NP on ultimate tensile strength.

## **RESULTS AND DISCUSSIONS:**

### **Tensile test result analysis:**

Figure 2 shows SEM images of Sn-58Bi and Sn-58Bi-xCo after reflow. There were two distinct phases in the microstructure: the darker phase was Sn-rich, while the brighter phase was Bi-rich. The structure of tin and bismuth were broken down and grain size was refined when Co NP was added to Sn-58Bi as shown in Figure 2 (b), (c), and (d). A similar result was also found when Ni was added into Sn-58Bi [29]. Researchers have also found similar alterations in the structure of the Sn-58Bi solder matrix after the addition of a third element [28, 33]. From Fig 2, it was observed that as the concentration of Co was increased, the grain size become smaller. As fine grain size was obtained, the tensile strength of the solder matrix was increased to a distinct value.

In previous studies, Co NP was added to Sn-based solder and it was found that the intermetallic compound formed by Co was thermodynamically more stable [31]. Co reduced the grain size and refined the interfacial IMC layers as well [31, 32]. In the current study, it was also observed in SEM images that the grain size inside the solder matrix significantly reduced which

enhanced the mechanical properties. The thermodynamic stability of IMC can promote equilibrium in structure [34] which significantly enhanced the mechanical properties.

The tensile test was performed on the prepared samples, and the results were summarized in Table 1. The tensile test result showed that the cobalt addition significantly increased the maximum stress of reflowed sample (Fig 3 a-d). After aging, it was observed that the maximum stress was decreased for all the samples, but the cobalt addition into the Sn-58Bi solder joint controlled the reduction of maximum stress significantly (Fig 3 a-d). The maximum stress values for all the samples are given in Table 1. The range of the tensile strain of the samples was observed between 3.58 mm to 6.57 mm. The stress-strain graph of Sn-58Bi with and without Co NP revealed that Co addition improved the stress and strain values. Co also controlled the reduction of maximum stress after the aging process. The Sn-58Bi-2Co has the highest strain value, the possible reason that improved the stress and strain of Sn-58Bi solder might be due to the refined grain structure [Fig 2 (b-d)]. The refined grain structure was also observed when Ni was added into Sn-58Bi [29, 35].

According to American Elements, the theoretical maximum tensile stress of the Sn-58Bi is between 51.5MPa and 55.4MPa [36]. However, the tensile strength obtained in this research work was higher than the theoretical value (71.25 MPa). Various temperatures and strain rates were studied by Chen et al. for the Sn-58Bi solder matrix [33]. The authors reported that when the strain rate was increased, the tensile strength also increased and the tensile strain was decreased. This indicates that the Sn-58Bi solder matrix was sensitive to the strain rate. The deformation mechanism of the Sn-58Bi was changed to gliding when a high strain rate is applied.

Fig. 4 shows the ultimate tensile strength versus aging time variation. From this, we concluded that when the Co concentration increased, the ultimate tensile strength was also increased. As the aging time increased, the ultimate tensile strength was decreased for all samples. The results

were summarized in Table 2. Sn-58 Bi had a tensile strength of 71.25 MPa, while Sn-58Bi-2Co had a tensile strength of 90.02 MPa. Based on these findings, the ultimate tensile strength of the Sn-58Bi was lower than the Sn-58Bi-2Co. Yang et al. studied the mechanical properties of Sn-58Bi and found that the ultimate tensile strength increased with increasing Ni concentration and reduced with increasing aging time [29]. This means that the concentration of the third element determined the ultimate tensile strength of the solder matrix [24]. It was significant that the Co concentration and aging time affect ductility substantially.

## **CONCLUSION:**

The effect of Co NP on the mechanical properties of Sn-58Bi was investigated. The tensile test was carried out to determine the effect of the Co NP on the tensile properties of the Sn-58Bi solder matrix at various aging times:

1. With the increase of Co NP concentration, the tensile strength was substantially increased to a significant value. The tensile test revealed that ductility was improved as the temperature was increased.
2. The tensile strength of Sn-58Bi (71.25 MPa) was lower than the Sn-58Bi-0.5Co (79.45 MPa), Sn-58Bi-1Co (84.63 MPa) and Sn-58Bi-2Co (90.02 MPa).
3. As the aging time increased, the ultimate tensile strength was decreased for all samples.

## **Acknowledgment:**

The financial support was provided by City, University of London, United Kingdom and University of Malaya, Kuala Lumpur, Malaysia.

## **Compliance with Ethical Standards:**

The authors followed the ethical standards during the experiments as well as during the preparation of the manuscript.

## **Author contribution:**

All authors have equal contribution.

## **Competing Interests:**

The authors have no relevant financial interests to disclose.

## **Research Data Policy and Data Availability:**

The current study is based on experimental data. In the manuscript, the experimental data were correlated and discussed with existing studies done by other researchers (given in the references). The experimental data of the current study is unpublished and will be provided for the evidences and for review.

## **References:**

1. Yunus, M., et al., Effect of voids on the reliability of BGA/CSP solder joints. *Microelectronics reliability*, 2003. **43**(12): p. 2077-2086.
2. Kang, S.K. and A.K. Sarkhel, Lead (Pb)-free solders for electronic packaging. *Journal of electronic materials*, 1994. **23**(8): p. 701-707.
3. Menon, S., et al., High lead solder (over 85%) solder in the electronics industry: RoHS exemptions and alternatives. *Journal of Materials Science: Materials in Electronics*, 2015. **26**(6): p. 4021-4030.
4. Ringgaard, E. and T. Wurlitzer, Lead-free piezoceramics based on alkali niobates. *Journal of the European Ceramic Society*, 2005. **25**(12): p. 2701-2706.
5. Su, L.-H., et al., Interfacial reactions in molten Sn/Cu and molten In/Cu couples. *Metallurgical and Materials Transactions B*, 1997. **28**(5): p. 927-934.
6. Choi, S., et al., Effects of Pb contamination on the eutectic Sn-Ag solder joint. *Soldering & Surface Mount Technology*, 2001.
7. Wood, E. and K. Nimmo, In search of new lead-free electronic solders. *Journal of Electronic Materials*, 1994. **23**(8): p. 709-713.
8. Mei, Z. and J. Morris, Characterization of eutectic Sn-Bi solder joints. *Journal of Electronic Materials*, 1992. **21**(6): p. 599-607.
9. Yang, C., L. Wang, and J. Wang, Fractures of ultra-low-k material in a chip during a flip-chip process. *Journal of Materials Science: Materials in Electronics*, 2022. **33**(2): p. 789-799.
10. Kang, S.K., et al., Microstructure and mechanical properties of lead-free solders and solder joints used in microelectronic applications. *IBM Journal of Research and Development*, 2005. **49**(4/5): p. 607.

11. Xu, K.-K., et al., Review of microstructure and properties of low temperature lead-free solder in electronic packaging. *Science and Technology of Advanced Materials*, 2020. **21**(1): p. 689-711.
12. Kotadia, H.R., P.D. Howes, and S.H. Mannan, A review: On the development of low melting temperature Pb-free solders. *Microelectronics Reliability*, 2014. **54**(6-7): p. 1253-1273.
13. Yao, P., P. Liu, and J. Liu, Effects of multiple reflows on intermetallic morphology and shear strength of SnAgCu-xNi composite solder joints on electrolytic Ni/Au metallized substrate. *Journal of Alloys and Compounds*, 2008. **462**(1-2): p. 73-79.
14. Jiang, N., et al., Influences of doping Ti nanoparticles on microstructure and properties of Sn58Bi solder. *Journal of Materials Science: Materials in Electronics*, 2019. **30**(19): p. 17583-17590.
15. Liu, Y., H. Zhang, and F. Sun, Solderability of SnBi-nano Cu solder pastes and microstructure of the solder joints. *Journal of Materials Science: Materials in Electronics*, 2016. **27**(3): p. 2235-2241.
16. Zhu, Z., Y.-c. Chan, and F. Wu. Effects of ZrO<sub>2</sub> nanoparticles on the mechanical properties of Sn 42 Bi 58 solder joint. in 2015 16th International Conference on Electronic Packaging Technology (ICEPT). 2015. IEEE.
17. Yang, L., et al., Influence of BaTiO<sub>3</sub> nanoparticle addition on microstructure and mechanical properties of Sn-58Bi solder. *Journal of Electronic Materials*, 2015. **44**(7): p. 2473-2478.
18. Lee, C.W., Y. Shin, and S. Yoo. Effect of SiC nanoparticles dispersion on the microstructure and mechanical properties of electroplated Sn-Bi solder alloy. in *Journal of Nano Research*. 2010. Trans Tech Publ.
19. Ma, Y., et al., Effects of graphene nanosheets addition on microstructure and mechanical properties of SnBi solder alloys during solid-state aging. *Materials Science and Engineering: A*, 2017. **696**: p. 437-444.
20. Kang, H., S.H. Rajendran, and J.P. Jung, Low melting temperature Sn-Bi solder: Effect of alloying and nanoparticle addition on the microstructural, thermal, interfacial bonding, and mechanical characteristics. *Metals*, 2021. **11**(2): p. 364.
21. Nai, S., J. Wei, and M. Gupta, Improving the performance of lead-free solder reinforced with multi-walled carbon nanotubes. *Materials Science and Engineering: A*, 2006. **423**(1-2): p. 166-169.
22. Liukui, G., et al., Effect of Rare Earth Y on Microstructure and Properties of Sn-58Bi Solder Alloy. *航空材料学报*, 2018. **38**(4): p. 101-108.
23. Chuang, T.-H. and H.-F. Wu, Effects of Ce addition on the microstructure and mechanical properties of Sn-58Bi solder joints. *Journal of electronic materials*, 2011. **40**(1): p. 71-77.
24. Zhou, S., et al., Effects of Ti addition on the microstructure, mechanical properties and electrical resistivity of eutectic Sn58Bi alloy. *Materials Science and Engineering: A*, 2019. **744**: p. 560-569.
25. Silva, B.L., et al., Cu and Ag additions affecting the solidification microstructure and tensile properties of Sn-Bi lead-free solder alloys. *Materials Science and Engineering: A*, 2017. **705**: p. 325-334.
26. Shafiq, I., et al. Electro-migration study of nano Al doped lead-free Sn-58Bi on Cu and Au/Ni/Cu ball grid array (BGA) packages. in 18th European Microelectronics & Packaging Conference. 2011. IEEE.
27. Shen, J., et al., Effects of minor Cu and Zn additions on the thermal, microstructure and tensile properties of Sn-Bi-based solder alloys. *Journal of Alloys and Compounds*, 2014. **614**: p. 63-70.
28. Gain, A.K. and L. Zhang, Growth mechanism of intermetallic compound and mechanical properties of nickel (Ni) nanoparticle doped low melting temperature tin-bismuth (Sn-Bi) solder. *Journal of Materials Science: Materials in Electronics*, 2016. **27**(1): p. 781-794.

29. Yang, L., et al., Effects of Ni addition on mechanical properties of Sn58Bi solder alloy during solid-state aging. *Materials Science and Engineering: A*, 2016. **667**: p. 368-375.
30. Bashir, M.N. and A. Haseeb, Improving mechanical and electrical properties of Cu/SAC305/Cu solder joints under electromigration by using Ni nanoparticles doped flux. *Journal of Materials Science: Materials in Electronics*, 2018. **29**(4): p. 3182-3188.
31. Bashir, M.N., et al., Effect of cobalt doping on the microstructure and tensile properties of lead free solder joint subjected to electromigration. *Journal of Materials Science & Technology*, 2016. **32**(11): p. 1129-1136.
32. Bashir, M.N. and A. Haseeb, Grain size stability of interfacial intermetallic compound in Ni and Co nanoparticle-doped SAC305 solder joints under electromigration. *Journal of Materials Science: Materials in Electronics*, 2022: p. 1-9.
33. Chen, X., et al., Mechanical deformation behavior and mechanism of Sn-58Bi solder alloys under different temperatures and strain rates. *Materials Science and Engineering: A*, 2016. **662**: p. 251-257.
34. Kane, R., B. Giessen, and N. Grant, New metastable phases in binary tin alloy systems. *Acta Metallurgica*, 1966. **14**(5): p. 605-609.
35. Glazer, J., Microstructure and mechanical properties of Pb-free solder alloys for low-cost electronic assembly: a review. *Journal of Electronic Materials*, 1994. **23**(8): p. 693-700.
36. Elements, A. Bismuth Tin Alloy. 2017, June 13 [cited 2022 March 27]; Available from: <https://www.americanelements.com/bismuth-tin-alloy-12010-55-8>.